

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 10-287775

(43)Date of publication of application : 27.10.1998

(51)Int.Cl.

C08L 23/08

C08L 23/10

(21)Application number : 09-095966

(71)Applicant : ASAHI CHEM IND CO LTD

(22)Date of filing : 14.04.1997

(72)Inventor : UCHIDA KENSUKE  
SHIBAYAMA SHINICHI

## (54) LOW-HARDNESS THERMOPLASTIC ELASTOMER COMPOSITION

## (57)Abstract:

PROBLEM TO BE SOLVED: To obtain a low-hardness thermoplastic elastomer compsn. which has improved processibility and degradation resistance and excellent mechanical properties by crosslinking a compsn. comprising a metallocene-catalyzed ethylene/ $\alpha$ -olefin elastomer, a hydrogenated vinylarom. compd./conjugated diene compd. block copolymer, a propylene polymer, and an oil.

SOLUTION: An ethylene/6-12C  $\alpha$ -olefin elastomer having a density of 0.8-0.9 g/cm<sup>3</sup> and a ratio of wt. average mol.wt. to number average mol.wt. (by GPC) lower than 3 is used as the ethylene/ $\alpha$ -olefin elastomer. A compsn. comprising 100 pts.wt. ethylene/ $\alpha$ -olefin elastomer, 5-100 pts.wt. hydrogenated vinylarom. compd./conjugated diene compd. block copolymer, 5-90 pts.wt. propylene polymer, and 52.5-250 pts.wt. oil for rubber is crosslinked with a free-radical initiator and a crosslinking aid to give the objective low-hardness thermoplastic elastomer compsn. Pref., the degree of crosslinking is 30% or higher in terms of heat resistance such as compression set.

## LEGAL STATUS

[Date of request for examination] 05.11.1999

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 3330840

[Date of registration] 19.07.2002

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]